JT SSh(B) 540-555W **Dual-glass Monocrystalline Solar Module**

144 Cells / MBB / Bifacial Mono PERC / 1500V DC / 21.5% Maximum Efficiency



QUALIFICATIONS & CERTIFICATES

- IEC 61215, IEC 61730, IEC 62941
- ISO 9001: Quality Management System
- ISO 14001: Environment Management System
- ISO 45001: Occupational Health and Safety

JETION SOLAR

As a member of CNBM - a Fortune 500 company, Jetion Solar provides various product solutions, global EPC service and financing. Its standard and high-efficiency product offerings are among the most powerful and cost-effective in the industry. Till now, Jetion Solar has cumulatively more than 15 GW module shipment and 1 GW global EPC track records.

KEY FEATURES



Maximum 1500V DC system voltage saves total system cost



High fire class


Fire class C certified, minimize the fire risk of the system

WARRANTY



30 Performance Warranty ears

Additional Value From Jetion Solar's Linear Warranty







Jetion Solar (China) Co., Ltd. Add: 1011 Zhencheng Road, Jiangyin, Jiangsu Province, P.R. China 214443

Tel: +86 (510) 8668 7300 400-8868-659 E-mail: marketing@ietion.com.cn Web: www.jetionsolar.com


IV Curves of JT540SSh(B) at different irradiances



IV Curves of JT540SSh(B) at different Temp







Section A-A

Remarks

ELECTRICAL DATA

TYPE (Tolerance:0-+5W)	JT540SSh(B)		JT545SSh(B)		JT550SSh(B)		JT555SSh(B)	
Test Condition	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT
Maximum Power Pmax (W)	540	403.26	545	407.29	550	411.34	555	415.40
Maximum Power Voltage Vmp (V)	41.7	39.0	41.9	39.2	42.1	39.4	42.3	39.6
Maximum Power Current Imp (A)	12.95	10.34	13.01	10.39	13.07	10.44	13.13	10.49
Open Circuit Voltage Voc (V)	50.0	46.6	50.2	46.8	50.4	47.0	50.6	47.2
Short Circuit Current Isc (A)	13.80	11.12	13.86	11.16	13.92	11.2	13.98	11.24
Module Efficiency (%)	20.	.9%	21	1%	21.	.3%	21.	5%

STC: Irradiance 1000W/m², Cell Temperature 25°C, Air Mass AM1.5

NMOT: Irradiance at 800W/m², Ambient Temperature 20°C, Wind Speed 1m/s

REAR SIDE POWER GAIN (JT540SSh(B))

Power Gain	5%	10%	15%	20%	25%	30%
Maximum Power - Pmax (W)	567	594	621	648	675	702
Maximum Power Voltage -Vmp (V)	41.70	41.70	41.70	41.80	41.80	41.80
Maximum Power Current -Imp (A)	13.60	14.25	14.90	15.51	16.15	16.79
Open Circuit Voltage -Voc (V)	49.60	49.60	49.60	49.70	49.70	49.70
Short Circuit Current -Isc (A)	14.45	15.10	15.75	16.36	17.00	17.64

TEMPERATURE RATINGS

Temperature Coefficient of Isc (alsc)	+0.048%/°C
Temperature Coefficient of Voc (βVoc)	-0.27%/°C
Temperature Coefficient of Pmax (γPmp)	-0.35%/°C
Normal Module Operating Temperature (NMOT)	41°C±3°C

OPERATING PARAMETERS

Maximum System Voltage	1500V/DC(IEC)
Operating Temperature	-40°C-+85°C
Maximum Series Fuse	25A
Maximum Test Load,Push/Pull	5400Pa/2400Pa
Conductivity at Ground	$\leq 0.1\Omega$
Safety Class	
Resistance	≥100MΩ
Voc and Isc Tolerance	±2%/±3%
Bifaciality	70±5%

MECHANICAL DATA

Solar Cell Type	Mono 91×182 mm(3.6×7.2 inches)
Number of Cells	144 [2 x (12 x 6)]
Module Dimensions	2278×1134×30 mm(89.7×44.6×1.2 inches)
Weight	32 kg(70.5 lb)
Front Cover	High transmission, AR coated tempered glass, 2.0mm
Back Cover	High transmission, Tempered, White Grid Glass/AR coating(optional), 2.0mm
Back Cover Frame	High transmission, Tempered, White Grid Glass/AR coating(optional), 2.0mm Silver, anodized aluminium alloy
Frame	Silver, anodized aluminium alloy
Frame J-Box	Silver, anodized aluminium alloy ≥IP68

PACKAGING CONFIGURATION

Module per pallet	36 pieces
Module per 40'HQ container	20 pallets, 720 pieces

*Installation instruction must be followed. See the installation manual or contact our technical service department for further information on approved installation. *The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement, Jetion Solar (China) Co., Ltd. reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datasheet which shall be duly incorporated into the binding contract made by the parties governing all transactions related to the purchase and sale of the products described herein. Jetion Solar_REV_2023_03_EN



Measuring tolerance: ±3%